

17360 : BASE 17369: CURING AGENT 97040

Description:	HEMPADUR ZINC 17360 is a two-component, zinc rich epoxy primer. It cures to a hard wearing and highly weather-resistant coating. Offers cathodic protection of local mechanical damage.
Recommended use:	As a "V.O.C.-compliant", versatile, long-term primer on steel for epoxy, vinyl and acrylic coating systems in medium to severely corrosive environments. In compliance with SSPC-Paint 20, type 2, level 2 and ISO 12944-5.
Service temperature:	Maximum, dry exposure only: 160°C/320°F
Certificates/Approvals:	Complies with EU Directive 2004/42/EC: subcategory j.
Availability:	Part of Group Assortment. Local availability subject to confirmation.

PHYSICAL CONSTANTS:

Shade nos/Colours:	19830* / Reddish grey
Finish:	Flat
Volume solids, %:	65 ± 2
Theoretical spreading rate:	13 m ² /l [521.3 sq.ft./US gallon] - 50 micron/2 mils
Flash point:	24 °C [75.2 °F]
Specific gravity:	2.8 kg/litre [23.1 lbs/US gallon]
Surface-dry:	15 minute(s) 20°C/68°F
Through-dry:	1.5 hour(s) 20°C/68°F
Fully cured:	7 day(s) 20°C/68°F
VOC content:	307 g/l [2.6 lbs/US gallon]
Shelf life:	1 year for BASE and 3 years (25°C/77°F) for CURING AGENT from time of production. <i>*other shades according to assortment list.</i>

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

APPLICATION DETAILS:

Version, mixed product:	17360
Mixing ratio:	BASE 17369: CURING AGENT 97040 4 : 1 by volume
Application method:	Airless spray / Air spray / Brush
Thinner (max.vol.):	08450 (5%) / 08450 (15%) / 08450 (5%) see REMARKS overleaf
Pot life:	2 hour(s) 20°C/68°F
Nozzle orifice:	0.017 - 0.021 "
Nozzle pressure:	150 bar [2175 psi] (Airless spray data are indicative and subject to adjustment)
Cleaning of tools:	HEMPEL'S TOOL CLEANER 99610
Indicated film thickness, dry:	50 micron [2 mils] see REMARKS overleaf
Indicated film thickness, wet:	75 micron [3 mils]
Overcoat interval, min:	see REMARKS overleaf
Overcoat interval, max:	see REMARKS overleaf

Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.
----------------	--

SURFACE PREPARATION: Remove oil and grease etc. thoroughly with suitable detergent. Remove salts and other contaminants by high pressure fresh water cleaning.
Abrasive blasting to Sa 2½ (ISO 8501-1:2007), SSPC-SP 10/ NACE No. 2, with a sharp-edged surface profile corresponding to Rugotest No. 3, BN10a-b, Keane-Tator Comparator, 3.0 G/S, 2-3 S, or ISO Comparator, Medium (G).

APPLICATION CONDITIONS: Use only where application and curing can proceed at temperatures above: -10°C/14°F. The temperature of the surface must also be above these limits. The temperature of paint itself should be 15°C/59°F or above. Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation.
In confined spaces provide adequate ventilation during application and drying.

SUBSEQUENT COAT: According to specification.

REMARKS: **Note:** If used as anticorrosive protection under insulation of high temperature equipment it is very important that NO moisture can penetrate during slow-down periods. This is to avoid the risk of "wet corrosion" when the temperature rises.

VOC - EU Directive 2004/42/EC:

Product	As supplied	15 vol. % thinning	Limit phase II, 2010
1736019830	307 g/l	389 g/l	500 g/l

For VOC of other shades, please refer to Safety Data Sheet.

Weathering/service temperatures: The natural tendency of epoxy coatings to chalk in outdoor exposure and to become more sensitive to mechanical damage and chemical exposure at elevated temperatures is also reflected in this product.

Stirring: Before mixing with the curing agent stir the base thoroughly in order to redisperse any possible settling after storage. After mixing it is equally important to maintain stirring to keep the wet paint as a homogeneous mixture.
This is specifically important in case of a high level of thinning and/or long break in application, where the risk of settlement of zinc particles is the highest.

Film thicknesses/thinning: May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and overcoating interval. Normal range dry is: 40-80 micron/1.6-3.2 mils. Thicknesses down to 15 micron/0.6 mils (extra thinning) and up to 80 micron/3.2 mils may be possible. This will alter spreading rate and may influence amount of thinning necessary, drying time, and recoating interval.
(The dry film thickness range does not take into account the correction factors for rough surfaces as listed in ISO 19840).

Overcoating: Overcoating intervals related to later conditions of exposure: If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
Before overcoating after exposure in contaminated environment, clean the surface thoroughly with high pressure fresh water hosing and allow drying.

A specification supersedes any guideline overcoat intervals indicated in the table.

Environment	Atmospheric, medium					
	-10°C (14°F)		0°C (32°F)		20°C (68°F)	
	Min	Max	Min	Max	Min	Max
HEMPADUR	18 h	Ext.*	9 h	Ext.*	2 h	Ext.*
HEMPATEX	18 h	72 h	9 h	36 h	2 h	8 h

NR = Not Recommended, Ext. = Extended, m = minute(s), h = hour(s), d = day(s)

Overcoating note: ***Depending on actual local conditions, the long maximum overcoating intervals may vary. Contact HEMPEL for more information.**
A completely clean surface is mandatory to ensure intercoat adhesion, especially at long overcoating intervals. Any dirt, oil, grease, and other foreign matter must be removed with suitable detergent followed by (high pressure) fresh water cleaning. Salts to be removed by fresh water hosing. In addition, scrubbing with a stiff brush may be necessary to remove zinc corrosion products (white rust). If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.

Note: **HEMPADUR ZINC 17360 For professional use only.**

ISSUED BY: HEMPEL A/S

1736019830

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.